

# **Advanced Materials**

# RenLam®/Ren® 1700-1 System

# GENERAL PURPOSE LAMINATING SYSTEM

#### **DESCRIPTION:**

RenLam<sup>®</sup>/Ren<sup>®</sup> 1700-1 system is an unfilled two-component general purpose laminating system that cures at room temperature. Low viscosity, a 20-minute gel time, excellent wet-out charasteristics, and controlles flow make RenLam<sup>®</sup>/Ren<sup>®</sup> 1700-1 system easy to apply and work with. This system was designed for hand lay-up applications and can be used for building tools, parts, and for repair work.

# **APPLICATIONS:**

RenLam<sup>®</sup>/Ren<sup>®</sup> 1700-1 system is well suited for patterns, drill jigs, assembly fixtures, Keller models, body cubes, draw dies, master dir models, spotting racks, etc.

#### **MIXING INSTRUCTIONS:**

Reaction Ratio 100R to 26H by weight

100R to 28H by volume

**Mixing**: Stir each component thoroughly before use. Weight each component accurately ( $\pm$  5%) into clean containers. Thoroughly mix resin and hardener together (minimum 3 minutes) scraping container sidewalls, bottom and mixing stick several times to assure a uniform mix.

# **TYPICAL MIXED PROPERTIES:**

Property
Gel time (4 fl. Oz.)
Color, mixed
Viscosity, mixed

(1) Tested @ 77 °F (25 °C)

ASTM Test Method
D-2471
20 minutes
Light yellow
2000 cP

Page 1/4
Distributed By
Freeman Manufacturing & Supply Co.
www.freemansupply.com 800-321-8511 FREEMAN



# **TYPICAL CURED PROPERTIES:**

\* Properties determined for a 10 oz. Glass cloth laminate.

Property	<b>ASTM Test Method</b>	Test Values (1)
Specific Gravity	D-792	1.13
Cubic inch per pound	D-792	18.5
Hardness (Shore D)	D-2240	90
Ultimate Compressive Strength (psi)	D-695	28,000
Ultimate Flexural Strength (psi)	D-790	37,000
Flexural Modulus* (psi)	D-790	1.55 x 10 <sup>6</sup>
Ultimate Tensile Strength (psi)	D-638	26,000
Deflection Temperature (264 psi) (°F)	D-648	128
Coefficient of Thermal Expansion (in/in/°F)	D-3386	1 x 10 <sup>-5</sup>
(1) Cure Schedule – 7 days @ 77 °F (25 °C), tested @ 77 °F		

NOTE: Typical Properties - These physical properties are reported as typical test values obtained by our test laboralory. If assistance is needed in establishing product specifications, please consult with our Quality Control Department.

#### **CURING INSTRUCTIONS:**

Although room temperature epoxies will normally set up to a rigid, demoldable state within 24 hours at room temperature (75 °F ± 5 °F), these systems reach their full cure after seven days at room temperature. A full cure can be accelerated by applying heat after the part has set rigid. We recommend a postcure of 150 °F for a minimum of six hours. (Add to this adequate time to bring the part to the postcure temperature.) After cure, the part should be cooled at a slow rate so as not to shock the part thermally.

Uniform heat distribution is also required during postcure; concentrated heat, such as that directed from a lamp, can cause warp. An elevated temperature cure will slighly increase the shrinkage compared to a room temperature cure.

# **HANDLING:**

# RenLam®/Ren® 1700-1 Resin and Hardener

Work in a well ventilated area and use clean, dry tools for mixing and applying. For two component system, combine the resin and hardener according to mix ratio. Mix together thoroughly and use immediately after mixing. Material temperature should not be below 18 °C (65 °F) when mixing.

# RenLam<sup>®</sup>/Ren<sup>®</sup> 1700-1 Resin

This product may crystallize upon storage. If crystallized, vent container and heat to 125-145 °F untif crystals dissolve. Stir well after product hasliquefied.





# **PACKAGING:**

This product is available in the following package sizes:

Small Preweighed Units : 6-qt. Resin / 6 preweighed hardener Pail Units : Pail Resin / appropriate hardener

Please call Customer Service (800) 367-8793 for price and availability

# STORAGE:

RenLam®/Ren® 1700-1 system should be stored in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and 104°F). Under these storage conditions, the shelf life is 2 years. The product should not be exposed to direct sunlight.

#### PRECAUTIONARY STATEMENT:

Huntsman Advanced Materials Americas LLC maintains up—to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement <u>prior to</u> using this material.

#### First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL AND INDUSTRIAL USE ONLY





# IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMIATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

RenLam/Ren is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices:
Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

Huntsman Advanced Technology Center 8600 Gosling Rd. The Woodlands Texas 77381 (281) 719-7400 Website: www.huntsman.com/advanced materials

