

Pro Glas 1200 SLOW UV EPOXY HARDENER



2:1

Description:

Pro Glas1200 is an extremely clear, tough, high gloss UV epoxy resin. 1200 has been formulated for improved UV resistance to reduce yellowing and surface degradation from UV exposure. 1200 has three hardeners, fast, medium and slow. Not recommended in freezing climates due to possibility of de-lamination.

Uses:

- Surfboard repair/manufacturing
- Wood boat construction
- General Purpose system easy mix 2:1
- Composite Parts
- Used to manufacture glues and compounds

TYPICAL PROPERTIES 100:50 volume

Uncured Curing Agent

SLOW

Mix ratio, ProGlas 1200 series	100A:50B
Gel Time 77° F	35-45 minutes
Thin Film Set Time / Hour	5

Handling Properties at 77 °F

Viscosity,	530 cps
Pot Life at 77 °F 150grams	40 minutes

Cured Resin¹

<u>Test</u>	<u>PROGLAS 1200 SLOW Value</u>
Durometer Hardness 2hr @ 60 C	82 +/- 3
Tensile strength, psi	7700
Flexural strength, psi	12,200
Flexural modulus	400,848
Tensile Elongation %	4.5
VOC (grams/liter)	0
Density Mixed (lbs/gal)	9.15

The information herein is general information designed to assist customers in determining whether ProGlas products are suitable to their applications. ProGlas products are intended for sale to industrial and commercial customers. We require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their specific applications. **Nothing herein constitute any warranty express or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Fiberlay Inc. - 24 S Idaho St Seattle WA, 98134 (800)942-0660

Pro Glas 1200 SLOW UV EPOXY HARDENER

Handling & Storage

All epoxy Resin/ Curing Agents, should be kept in tightly closed containers in a cool, dry place. Product will absorb moisture and carbon dioxide which may affect viscosity or create foaming when reacted with Resin/Curing Agents. This product will have a minimum shelf life of one year if properly stored in unopened containers.

To ensure maximum stability and maintain optimum resin properties, resins should be stored in closed containers at temperatures below 75°F and away from heat sources and sunlight. All storage areas and containers should conform to local fire and building codes. Inventory levels should be kept to a reasonable min with first-in, first-out stock rotation.

Safety

Read and understand the Material Safety Data Sheet before working with this product

The information herein is general information designed to assist customers in determining whether ProGlas products are suitable to their applications. ProGlas products are intended for sale to industrial and commercial customers. We require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their specific applications. **Nothing herein constitute any warranty express or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Fiberlay Inc. - 24 S Idaho St Seattle WA, 98134 (800)942-0660